

Test Report

Report No. : AGC05443231012-001

SAMPLE NAME: Wireless charger

MODEL NAME : MO2220

APPLICANT: MID OCEAN BRANDS B.V

STANDARD(S) : Please refer to the following page(s).

DATE OF ISSUE : Oct. 19, 2023

Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd.





Applicant : MID OCEAN BRANDS B.V

Address : 7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong.

Test Site : 6/F., Building 2, Sanwei Chaxi Industrial Park, Sanwei Community, Hangcheng Street,

Bao'an District, Shenzhen, Guangdong, China

Report on the submitted sample(s) said to be:

Sample Name : Wireless charger

Model : MO2220
Vendor code : 114276
Country of Origin : CHINA
Country of Destination : EUROPE
Sample Received Date : Oct. 11, 2023

Testing Period : Oct. 11, 2023 to Oct. 19, 2023

Test Requested : Selected test(s) as requested by client.

Test Requested: Conclusion

2011/65/EU (RoHS) and its amendment directive (EU) 2015/863 - Pb, Cd, Hg, Cr⁶⁺, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Pass

Report No.: AGC05443231012-001

Regulation (EU) 2019/1021 on persistent organic pollutants (POPs)

- Pentachlorophenol (PCP) Content

Pass

- Formaldehyde Release Pass

Approved by : Jossie Liang

Liangdan, Jessie.Liang

Technical Director




Report Revise Record

Report No.: AGC05443231012-00)1
-------------------------------	----


Report Version	Issued Date	Valid Version	Notes
/	Oct. 19, 2023	Valid	Initial release










AGC





Report No.: AGC05443231012-001
















20 10 100 80 70 60 O unu

Report No.: AGC05443231012-001

50 40

O SO 30 40 20 60 10 80 90100 10 SO 30 40 20 60 10 80 90 50

10 20 30 40 50 60 70 80 90100 10 20 30 40 50 60

The photo of AGC05443231012-001 is for use only with the original report.

Test Point Description

Test point	Test module	Test parts	Test point description
Wireless char	rger		
1			Black plastic shell
2			White glue
3		Outer shell	Double-sided tape
4			Woody shell
5			Silver metallic sheet
6			Grey ceramic
7		Induction coil	Wire jacket in the coil
8			Enameled wire
9		Thermistor	Black thermistor body
10		Inermistor	Enameled wire
11		Canaditana	Red plastic shell
12		Capacitance	Film
13			Chip capacitor
14			Chip resistor
15	Circuit board		Chip diode
16	Circuit board		Chip triode
17			IC body
18			Metallic pin with solder
19			PCB
20			Solder
21			USB metal plug
22		USB plug	White plastic plug
23			Metal pin
24			Chip capacitor
25			Chip resistor
26			Metal pin
27		Type-C plug	Metallic pogopin
28			Grey plastic plug



29		White plastic plug
30		Type-C metal plug
31		White inner glue
32		Black handle
33	 	PCB
34	 	Solder
35		Black outer wire jacket
36		Brown enameled wire
37	 Wire rod	Green enameled wire
38		Blue enameled wire
39		Red enameled wire
1-4	 	Woody shell

Note: "---" = The test point exists alone in the sample and is not attached to the test module or test parts.



Note: N.D.=Not Detected (less than method detection limit), MDL = Method Detection Limit, 1mg/kg=0.0001%

2011/65/EU (RoHS) and its amendment directive (EU) 2015/863

- Pb, Cd, Hg, Cr⁶⁺, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Test Item	Test Method/ Instrument	MDL	Maximum Limit
Lead (Pb)		/	1000mg/kg
Cadmium (Cd)		/	100mg/kg
Mercury (Hg)	IEC 62321-3-1:2013/ XRF	/	1000mg/kg
Total Chromium		/	/
Total Bromine		/	/
Chemistry Method		•	
Lead (Pb)	IEC 62321-5:2013/ ICP-OES	2mg/kg	1000mg/kg
Cadmium (Cd)	IEC 62321-5:2013/ ICP-OES	2mg/kg	100mg/kg
Mercury (Hg)	IEC 62321-4: 2013+A1:2017/ ICP-OES	2mg/kg	1000mg/kg
Non-metal: Hexavalent Chromium (Cr ⁶⁺)	IEC 62321-7-2:2017/ UV-Vis	8mg/kg	1000mg/kg
Metal: Hexavalent Chromium (Cr ⁶⁺)	IEC 62321-7-1:2015/ UV-Vis	0.1μg/cm ²	/
-Monobromobiphenyl (MonoBB) -Dibromobiphenyl (DiBB) -Tribromobiphenyl (TriBB) -Tetrabromobiphenyl (TetraBB) -Pentabromobiphenyl (PentaBB) -Hexabromobiphenyl (HexaBB) -Heptabromobiphenyl (HeptaBB) -Octabromobiphenyl (OctaBB) -Nonabromodiphenyl (NonaBB) -Decabromodiphenyl (DecaBB)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg
PolybrominatedDiphenylethers (PBDEs) -Monobromodiphenyl ether (MonoBDE) -Dibromodiphenyl ether (DiBDE) -Tribromodiphenyl ether (TriBDE) -Tetrabromodiphenyl ether (TetraBDE) -Pentabromodiphenyl ether (PentaBDE) -Hexabromodiphenyl ether (HexaBDE) -Heptabromodiphenyl ether (HeptaBDE) -Octabromodiphenyl ether (OctaBDE) -Nonabromodiphenyl ether (NonaBDE) -Decabromodiphenyl ether (DecaBDE)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg
Di-iso-butyl phthalate (DIBP)		50mg/kg	1000mg/kg
Dibutyl phthalate (DBP)		50mg/kg	1000mg/kg
Butylbenzyl phthalate (BBP)	IEC 62321-8:2017/ GC-MS	50mg/kg	1000mg/kg
Di-(2-ethylhexyl) Phthalate (DEHP)		50mg/kg	1000mg/kg



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443231012-00
	I	' b	BL	/	
	(Cd	BL	/	
	F	łg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
1	Br	PBBs PBDEs	BL	/	Conformity
_	Dl	BP	N/A	N.D.	
		BP	N/A	N.D.	
_		BP	N/A	N.D.	
	DE	ЕНР	N/A	N.D.	
	F	P b	BL	/	
		Cd	BL	/	
	ŀ	Ig	BL	/	
		Cr^{6+})	BL	/	
2	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
3	Br	PBBs PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
	DBP		N/A	N.D.	
_		BP	N/A	N.D.	
_	DEHP		N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
			BL	/	
_		Cr ⁶⁺)	BL	/	
4	Br	PBBs PBDEs	BL	/	Conformity
-	Di	BP	N/A	N.D.	
-		BP	N/A	N.D.	
-		BP	N/A	N.D.	
-		EHP	N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443231012-00
	F	' b	BL	/	
	(Cd	BL	/	
	F	łg	BL	/	
	Cr(Cr ⁶⁺)	IN	N.D.	
5	Br	PBBs PBDEs	N/A	/	Conformity
	DI	BP	N/A	/	
		BP	N/A	/	
		BP	N/A	/	
		EHP	N/A	/	
		Pb	BL	/	
		Cd Cd	BL	/	
-		Ig	BL	/	
		Cr ⁶⁺)	BL	/	
6	Br	PBBs PBDEs	BL	/	Conformity
-	DIBP		N/A	N.D.	
-	DBP		N/A	N.D.	
_	BBP		N/A	N.D.	
	DEHP		N/A	77	
	Pb		BL	//	
	Cd		BL	/	
-	Hg		BL	/	
-	Cr(Cr ⁶⁺)		BL	/	
7	Br	PBBs	IN	N.D.	Conformity
_	Di	PBDEs	NT/A	N.D.	
		BP	N/A	N.D.	
	DBP		N/A	N.D.	
	BBP DEHP		N/A	N.D.	
			N/A	N.D.	
		Pb	BL	/	
		Cd .	BL	/	
_		Ig	BL	/	
_	Cr(Cr ⁶⁺)	BL	/	
8	Br	PBBs PBDEs	BL /		Conformity
	Dl	BP	N/A	N.D.	
	D	BP	N/A	N.D.	
Γ	В	BP	N/A	N.D.	
	DE	ЕНР	N/A	80	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443231012-00
	I	Pb	BL	/	
	(Cd	BL	/	
		łg	BL	/	
	Cr(Cr ⁶⁺)	IN	N.D.	
9	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP	N/A	N.D.	
		Pb	BL	/	
_		Cd	BL	/	
		Ig	BL	/	
-		Cr ⁶⁺)	BL	/	
10	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
-	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
11	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
	DEHP		N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Ig	BL	/	
		Cr ⁶⁺)	BL	/	
12	Br	PBBs PBDEs	BL	/	Conformity
<u> </u>	Di	IBP	N/A	N.D.	
-		BP	N/A	N.D.	
-		BP	N/A	N.D.	
-		EHP	N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443231012-00
	I	Pb	BL	/	
	(Cd	BL	/	
		łg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
13	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Ig	BL	/	
		Cr ⁶⁺)	BL	/	
14		PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
15	Br	PBBs PBDEs	IN	N.D. N.D.	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
			N/A	N.D.	
	BBP DEHP		N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		I g	BL	/	
		Cr ⁶⁺)	BL	/	
16	Br	PBBs PBDEs	BL	/	Conformity
	D	BP	N/A	N.D.	
		BP	N/A	N.D.	
-		BP	N/A N/A	N.D.	
		EHP	N/A N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443231012-00
		Pb	BL	/	
		Cd	BL	/	
]	Hg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
17	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP	N/A	N.D.	
		Pb	BL	/	
			BL	/	
		Hg	BL	/	
		Cr ⁶⁺)	BL	/	
18	Br	PBBs PBDEs	N/A	/	Conformity
-	DIBP		N/A	N.D.	
_	DBP		N/A	N.D.	
_	BBP		N/A	N.D.	
_	DEHP		N/A	N.D.	
	Pb		BL	/	
_	Cd		BL	/	
_	Hg		BL	/	
_	$Cr(Cr^{6+})$		BL	/	
_	PRRs			N.D.	
19	Br	PBDEs	IN	N.D.	Conformity
-	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
	DEHP		N/A	N.D.	
		Pb	BL	/	
_		Cd	BL	/	
_		Hg	BL	/	
-		Cr ⁶⁺)	BL	/	
-		PBBs		/	
20	l Rr	PBDEs	N/A	/	Conformity
-	D	IBP	N/A	N.D.	
-		BP	N/A	N.D.	
-		BP	N/A	N.D.	
-		ЕНР	N/A	N.D.	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Cos443231012-00
	F	b	BL	/	
	(Cd	BL	/	
	F	Ig	BL	/	
	Cr($\mathbb{C}r^{6+}$)	BL	/	
21	Br	PBBs	N/A	/	Conformity
_		PBDEs		/	J
_		BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		CHP	N/A	N.D.	
		b	BL	/	
	(Cd Cd	BL	/	
		[g	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
22	Br	PBBs	BL	/	Conformity
		PBDEs	27/4	/	•
_	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
_	BBP		N/A	N.D.	
		HP	N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
23	Br	PBBs PBDEs	N/A	/	Conformity
	DI	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP EHP	N/A	N.D.	
		b	BL	/	
		Cd Cd	BL	/	
	Hg		BL	/	
		Cr^{6+}	BL	/	
24	Br	PBBs	BL	/	Conformity
-	Di	PBDEs	NT/A	/ N.D.	j
<u> </u>		BP	N/A	N.D.	
<u> </u>		BP	N/A	N.D.	
_		BP	N/A	N.D.	
	DE	EHP	N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443231012-00
	I	P b	BL	/	
	(Cd	BL	/	
	F	łg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
25	Br	PBBs PBDEs	BL	/	Conformity
	D	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP	N/A	N.D.	
		Pb	BL	/	
		Cd Cd	BL	/	
		Ig	BL	/	
		Cr ⁶⁺)	BL	/	
26	Br	PBBs PBDEs	N/A	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	154	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		IN	N.D.	
27	Br	PBBs PBDEs	N/A	/	Conformity
	Dì	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
	DEHP		N/A	54	
		Pb	BL	/	
		Cd	BL	/	
		Нg	BL	/	
		Cr ⁶⁺)	BL	/	
28	Br	PBBs PBDEs	BL	/	Conformity
-	D ₁	IBP	N/A	N.D.	
-		BP	N/A	N.D.	
-		BP	N/A	N.D.	
<u> </u>		EHP	N/A	N.D.	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443231012-00
	I	Pb	BL	/	
	Cd		BL	/	
	F	łg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
29	Br PBBs PBDEs		BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Ig	BL	/	
		Cr ⁶⁺)	IN	N.D.	
30	Rr PB	PBBs PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
-		EHP	N/A	/	
		Pb	BL	/	
		Cd	BL	/	
		I g	BL	/	
	Cr(Cr ⁶⁺)		BL	/	
31	Br PBBs PBDEs		BL	/	Conformity
	D	IBP	N/A	N.D.	
	DBP		N/A	N.D.	
		BP	N/A	N.D.	
	DEHP		N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		I g	BL	/	
		Cr ⁶⁺)	BL	/	
32	Br	PBBs	BL	/	Conformity
-	PBDEs			/ N.D.	
-	DIBP		N/A	N.D.	
-	DBP		N/A	N.D.	
		BP EHP	N/A N/A	N.D.	



Test point Test Item		Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	Pb		BL	/			
	Cd		BL	/			
	Hg		BL	/			
		Cr ⁶⁺)	BL	/			
22		PBBs	DI	N.D.	Conformity		
33	Br	PBDEs	IN	N.D.			
	D	IBP	N/A	N.D.			
	D	BP	N/A	N.D.			
	В	BP	N/A	N.D.			
	DI	ЕНР	N/A	N.D.			
]	Pb	BL	/			
	(Cd	BL	/			
	I	Hg	BL	/			
		Cr ⁶⁺)	BL	/			
		PBBs		/	Conformity		
34	Br	PBDEs	N/A	/			
	DIBP		N/A	/			
	DBP		N/A	/			
	BBP		N/A	/			
	DEHP		N/A	/			
		Pb	BL	/			
		Cd	BL	/			
			BL	/			
-	$Cr(Cr^{6+})$		BL	/	Conformity		
35	Br PBBs PBDEs		BL	/			
	D	IBP	N/A	N.D.			
	DBP		N/A	N.D.			
		BP	N/A	N.D.	-		
		EHP	N/A	N.D.			
		Pb	BL	/			
-		Cd	BL	/			
-		-Ig	BL	/			
36	$\frac{\text{Trg}}{\text{Cr}(\text{Cr}^{6^+})}$		BL	/			
	Br PBBs PBDEs			/			
			- BL	/	- Conformity		
	DIBP		N/A	N.D.			
	DBP		N/A	N.D.			
	BBP		N/A	N.D.			
-		ЕНР	N/A	66			



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion	
	Pb		BL	/		
	Cd		BL	/		
	Hg		BL	/		
	Cr(Cr ⁶⁺)		BL	/		
37	Br	PBBs	BL	/	Conformity	
37	ВГ	PBDEs	BL	/		
	D	IBP	N/A	N.D.		
	Г	BP	N/A	N.D.		
	В	BP	N/A	N.D.		
	D	ЕНР	N/A	N.D.		
	Pb Cd		BL	/	Conformity	
			BL	/		
	Hg		BL	/		
20	$Cr(Cr^{6+})$		BL	/		
	Br PBBs PBDEs		- BL -	/		
38				/		
	DIBP		N/A	N.D.		
	DBP		N/A	N.D.		
	BBP		N/A	N.D.		
	DEHP		N/A	N.D.		
39	Pb Cd		BL	/		
			BL	/		
	Hg		BL	/		
	Cr(Cr ⁶⁺)		BL	/		
	PRRs	BL	/	Conformity		
	Br PBDEs		/			
	DIBP		N/A		N.D.	
	DBP		N/A		N.D.	
	BBP DEHP		N/A	N.D.		
			N/A	N.D.		

Element	Unit	Non-metal	Metal	Composite Material
Cd	mg/kg	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤50-3σ <x <150+3σ≤OL</x
Pb	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Hg	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Cr	mg/kg	BL≤700-3σ <x< td=""><td>BL≤700-3σ<x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<></td></x<>	BL≤700-3σ <x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<>	BL≤500-3σ <x< td=""></x<>



Report No.: AGC05443231012						
Br	mg/kg	BL≤300-3σ <x< th=""><th>N/A</th><th>BL≤250-3σ<x< th=""></x<></th></x<>	N/A	BL≤250-3σ <x< th=""></x<>		

Remark:

- (1) BL= Below Limit, OL= Over limited, IN = Inconclusive, Scanning by XRF and detected by chemical method, N/A = Not applicable.
- (2) Results were obtained by XRF for primary scanning, and further chemical testing by ICP (for Cd, Pb, Hg), UV-Vis (for Cr(VI)) and GC-MS (for PBBs, PBDEs) are recommended to be performed, if the concentration exceeds the above warning value.
- (3) The XRF scanning test for RoHS elements The reading may be different to the actual content in the sample be of non-uniformity composition.
- (4) Boiling-water-extraction:(X represents the results of the tested sample)

Number	Colorimetric result (Cr(VI) concentration)	Judgement
1	$X \le 0.1 \mu g/cm^2$	Negative
2	$0.1 \mu g/cm^2 \le X \le 0.13 \mu g/cm^2$	Uncertainty
3	$X > 0.13 \mu g/cm^2$	Positive

Negative indicates the absence of Cr(VI) on the tested areas concentration is below the limit of quantification. The coating is considered a non-Cr(VI) based coating.

Uncertainty indicates the absence of Cr(VI) on the tested areas unavoidable coating variations may influence the determination.

Positive indicates the presence of Cr(VI) on the tested areas concentration is above the limit of quantification and the statistical margin of error. The sample coating is considered to contain Cr(VI).

Storage conditions and production date of the tested sample are unavailable and thus result of Cr(VI) represent status of the sample at the time of testing.

(5) Disclaimers: This XRF Scanning report is for reference purposes only. The applicant shall make its/his/her own judgment as to whether the information provided in this XRF screening report is sufficient for its/his/her purposes. The result shown in this XRF scanning report will differ based on various factors, including but not limited to, the sample size, thickness, area, surface flatness, equipment parameters and matrix effect (e.g. plastic, rubber, metal, glass, ceramic etc.). Further wet chemical pre-treatment with relevant chemical equipment analysis are required to obtain quantitative data.



Regulation (EU) 2019/1021 on persistent organic pollutants (POPs)

- Pentachlorophenol (PCP) Content

Test Methods and Equipment: EPA 3550C:2007 & EPA 8270E:2018; GC-MS


Test Item(s)	Unit Limit	Limit	MDL	Test Result(s)
Test tieni(s)		Liiiit		1-4
Pentachlorophenol (PCP)	mg/kg	5	5	N.D.
Со	Conformity			


- Formaldehyde Release

Test Methods and Equipment: EN 717-3:1996; UV-Vis

Test Item(s)	Unit	Client's limit	MDL	Test Result(s)
Test Item(s)				1-4
Formaldehyde Release	mg/kg	80	1	N.D.
Со	Conformity			


Test Flow Chart of XRF









Test Flow Chart of Phthalates









Test Flow Chart of Hexavalent Chromium (Cr6+)








Test Flow Chart of PBBs and PBDEs









Test Flow Chart of Hexavalent Chromium (Cr6+)




Test Flow Chart of REACH SVHC









Test Flow Chart of REACH SVHC









Test Flow Chart of Phthalates









Test Flow Chart of PBBs and PBDEs









Test Flow Chart of Hexavalent Chromium (Cr6+)









Test Flow Chart of Hexavalent Chromium (Cr6+)








Test Flow Chart of Lead, Cadmium and Mercury





These sample were dissolved totally by pre-conditioning method according to above flow chart






Test Flow Chart of Pentachlorophenol (PCP)







Test Flow Chart of Formaldehyde Release





Conditions of Issuance of Test Reports

- 1. All samples and goods are accepted by the Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd. (the "Company") solely for testing and reporting in accordance with the following terms and conditions. The company provides its services on the basis that such terms and conditions constitute express agreement between the company and any person, firm or company requesting its services (the "Clients").
- 2. Any report issued by Company as a result of this application for testing services (the "Report") shall be issued in confidence to the Clients and the Report will be strictly treated as such by the Company. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of the Company. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Company to its customer, supplier or other persons directly concerned. The Company will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the Report, unless required by the relevant governmental authorities, laws or court orders.
- 3. The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.
- 4. In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate.
- 5. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.
- 6. The Company will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations. 7. Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.
- 8. The Company is not responsible for recalling the electronic version of the original report when any revision is made to them. The Client assumes the responsibility to providing the revised version to any interested party who uses them.
- 9. Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.

*** End of Report ***