

Test Report

Report No. : AGC05443231125-001

SAMPLE NAME : Tritan Renew bottle with cork lid 500 ml

MODEL NAME : MO2266

APPLICANT: MID OCEAN BRANDS B.V

STANDARD(S) : Please refer to the following page(s).

DATE OF ISSUE : Nov. 27, 2023

Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd.





Applicant : MID OCEAN BRANDS B.V

Address : 7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong.

Test Site : 6/F., Building 2, Sanwei Chaxi Industrial Park, Sanwei Community, Hangcheng Street,

Bao'an District, Shenzhen, Guangdong, China

Report on the submitted sample(s) said to be:

Sample Name : Tritan Renew bottle with cork lid 500 ml

Model : MO2266
Vendor code : 114276
Country of Origin : CHINA
Country of Destination : EUROPE
Sample receiving state : Normal

Sample Received Date : Nov. 17, 2023

Testing Period : Nov. 17, 2023 to Nov. 27, 2023

Test Requested : Selected test(s) as requested by client.

Approved by : Jessie liang

Liangdan, Jessie.Liang

Report No.: AGC05443231125-001

Technical Director



Report No.: AGC05443231125-001 Conclusion Mechanical dishwashing safe test Pass Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 63 Pass - Lead(Pb) Content Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 23 **Pass** -Cadmium(Cd) Content Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 51&52 **Pass** - Phthalates Content Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50 **Pass** - Polycyclic-aromatic Hydrocarbons (PAHs) Content Regulation (EU) 2019/1021 on persistent organic pollutants (POPs) **Pass** - Pentachlorophenol (PCP) Content - Formaldehyde Release Pass German Food, Articles of Daily Use and Feed Code of September, 2005(LFGB), Section 30 & 31, and BfR recommendation IX, Regulation 1935/2004/EC, Regulation (EU) No 10/2011 and its amendment Regulation (EU) 2020/1245 - Overall migration **Pass** - Bisphenol A(BPA) content **Pass** - Specific migration of Bisphenol A(BPA) **Pass** - Specific migration of Heavy metals Pass -Specific migration of Primary aromatic amines Pass

DM-4B-COM-003-v01 for:

-Volatile Organic Matter
- Peroxide value
- Specific Migration of Organotin (measured as Tin)

Pass
Pass



Report Revise Record

Report Version	Issued Date	Valid Version	Notes
/	Nov. 27, 2023	Valid	Initial release



The photo of the sample

The photo of AGC05443231125-001 is for use only with the original report.

Test Point Description

Test point	Test point description
1-1	Transparent blue bottle body
1-2	Grey silicone cover
1-3	Wooden cover



Note: N.D.=Not Detected (less than method detection limit), MDL = Method Detection Limit, 1mg/kg=0.0001%

Mechanical dishwashing safe test

Test Result of mechanical dishwashing safe test:

Requirements:For dishwasher safe test, if there is no noticeable change in appearance (e.g. color, size and shape) and function, it should be "PASS",

Sample No.: Blue bottle body

Test method: Refer BS EN 12875 -1-2005

Washing temperature: 60°C Number of cycle: 10 cycles

Number of tested sample: 2 pc(s). Number of control sample: 1 pc(s).

For all tested plastic or metal articles:

No visible change of color, gloss and clouding was found on the tested samples after wash.

No visible deposit or iridescent layer was found on the tested samples after wash.

No visible swelling, deformation, cracking, crazing or delamination was found on the tested samples after wash.

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 63

- Lead(Pb) Content

Test Methods and Equipment: CPSC-CH-E1002-08.3; ICP-OES

Tost Itam(s)	Unit	Limit	MDI	Test Result(s)		
Test Item(s)	Onit	Lillit	Limit MDL	1-1	1-2	1-3
Lead(Pb)	mg/kg	500	10	N.D.	N.D.	N.D.
Conclusion			Conformity	Conformity	Conformity	

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 23

-Cadmium(Cd) Content

Test Methods and Equipment: IEC 62321-5:2013; ICP-OES

Test Item(s)	Unit Limit	MDL	Test Result(s)		
		Lillit	MDL	1-1	1-2
Cadmium(Cd)	mg/kg	100	10	N.D.	N.D.
Co	Conformity	Conformity			



Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 51&52

- Phthalates Content

Test Methods and Equipment: IEC 62321-8:2017; GC-MS

Tost Itom(s)	Unit Limit		MDL	Test Result(s)	
Test Item(s)	Unit	Limit	MDL	1-1	1-2
Diisobutyl phthalate (DIBP) CAS:84-69-5	%	0.1	0.005	N.D.	N.D.
Dibutyl phthalate (DBP) CAS:84-74-2	%	0.1	0.005	N.D.	N.D.
Butylbenzyl phthalate (BBP) CAS:85-68-7	%	0.1	0.005	N.D.	N.D.
Di-(2-ethylhexyl) Phthalate (DEHP) CAS:117-81-7	%	0.1	0.005	N.D.	N.D.
Di-n-octyl phthalate (DNOP) CAS:117-84-0	%	/	0.005	N.D.	N.D.
Di-isononyl phthalate (DINP) CAS:28553-12-0, 68515-48-0	%	/	0.005	N.D.	N.D.
Di-isodecyl phthalate(DIDP) CAS:26761-40-0, 68515-49-1	%	/	0.005	N.D.	N.D.
Sum of DIBP +DBP+BBP+DEHP	%	0.1	/	N.D.	N.D.
Sum of DNOP+DINP+DIDP	%	0.1	/	N.D.	N.D.
Con	Conformity	Conformity			

Limit requirements of Phthalates

Toys and childcare articles	Each of DEHP, DBP, BBP, DIBP is less than 0.1% or the sum of DEHP+DBP+BBP+DIBP is less than 0.1%
Toys and childcare articles which can be placed in the mouth by children	The sum of DINP+DIDP+DNOP is less than 0.1%

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50

- Polycyclic-aromatic Hydrocarbons (PAHs) Content

Test Methods and Equipment: Afps GS 2019:01 PAK; GC-MS

Tost Itam(s)	Unit	Limit	MDL	Test Result(s)		
Test Item(s)	Unit	LIIIII	MDL	1-1	1-2	
Benzo[a]pyrene(BaP)	mg/kg	1	0.1	N.D.	N.D.	
Benzo[e]pyrene(BeP)	mg/kg	1	0.1	N.D.	N.D.	
Benzo[a]anthracene(BaA)	mg/kg	1	0.1	N.D.	N.D.	
Benzo[b]fluoranthene(BbF)	mg/kg	1	0.1	N.D.	N.D.	
Benzo[j]fluoranthene(BjFA)	mg/kg	1	0.1	N.D.	N.D.	
Benzo[k]fluoranthene(BkF)	mg/kg	1	0.1	N.D.	N.D.	
Chrysene(CHR)	mg/kg	1	0.1	N.D.	N.D.	
Dibenzo[a,h]anthracene(DBA)	mg/kg	1	0.1	N.D.	N.D.	
Co	Conclusion					

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Report No.: AGC05443231125-001



Limit requirements of Polycyclic-aromatic Hydrocarbons (PAHs) (Unit: mg/kg)

Items	CAS No.	Extender oils or used for the production of tyres or parts of tyres	Any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity	Toys, including activity toys, and childcare articles, any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity
Benzo[a]pyrene(BaP)	50-32-8	≤1	≤ 1	≤ 0.5
Benzo[e]pyrene(BeP)	192-97-2	/	≤ 1	≤ 0.5
Benzo[a]anthracene(BaA)	56-55-3	/	≤ 1	≤ 0.5
Benzo[b]fluoranthene(BbF)	205-99-2	/	≤ 1	≤ 0.5
Benzo[j]fluoranthene(BjFA)	205-82-3	/	≤ 1	≤ 0.5
Benzo[k]fluoranthene(BkF)	207-08-9	/	≤ 1	≤ 0.5
Chrysene(CHR)	218-01-9	/	≤ 1	≤ 0.5
Dibenzo[a,h]anthracene(DBA)	53-70-3	/	≤ 1	≤ 0.5
Sum of BaP+ BeP+ BaA+ BbF+ BjFA+ BkF+ CHR+ DBA	/	≤ 10	/	/

Regulation (EU) 2019/1021 on persistent organic pollutants (POPs)

- Pentachlorophenol (PCP) Content

Test Methods and Equipment: EPA 3550C:2007 & EPA 8270E:2018; GC-MS

Test Item(s)	Unit	Limit	MDL	Test Result(s)
	Oilit	LIIIII	MDL	1-3
Pentachlorophenol (PCP)	mg/kg	5	5	N.D.
Со	Conformity			

- Formaldehyde Release

Test Methods and Equipment: EN 717-3:1996; UV-Vis

Tost Itom(s)	Unit	Client's	MDL	Test Result(s)
Test Item(s)	Onit	limit	MIDL	1-3
Formaldehyde Release	mg/kg	80	1	N.D.
Co	Conformity			



		Test		
Test point		Overall migra	Conclusion	
		3% Acetic acid, 70°C,2h	50% Ethanol, 70°C,2h	
	1 st migration	N.D.	N.D.	
1-1	2 nd migration	N.D.	N.D.	Conformity
	3 rd migration	N.D.	N.D.	
	Limit	10	10	/
	MDL	5	5	/

	Test		
Test point	Overall migra	Conclusion	
	3% Acetic acid, 70°C,2h	50% Ethanol, 70°C,2h	
1-2	N.D.	N.D.	Conformity
Limit	10	10	/
MDL	5	5	/

- Bisphenol A(BPA) content

Test Item	Bisphenol A (BPA)
Limit(Client's Requirement) (mg/kg)	Absent
MDL(mg/kg)	0.1
Test Method/Instrument	EPA 3540C:1996& EPA 8321B:2007/ LC-MS-MS

Test point	Test Result (mg/kg)	Conclusion
	Bisphenol A (BPA)	Conclusion
1-2	N.D.	Conformity




Test Item	Bisphenol A (BPA)		
Limit(mg/kg)	Absent		
MDL (mg/kg)	0.1		
Test Method/Instrument	EPA 3540C:1996& EPA 8321B:2007/ LC-MS-MS		

Test point	Test Result (mg/kg)	Conclusion
Test point	Bisphenol A (BPA)	Conclusion
1-1	N.D.	Conformity

- Specific migration of Bisphenol A(BPA)

	Test Result	
Test point	Specific migration of Bisphenol A(BPA)/ (mg/kg)	Conclusion
	3% Acetic acid,70°C,2h	
1 st migration	N.D.	
2 nd migration	N.D.	Conformity
3 rd migration	N.D.	
Limit	0.05	/
MDL	0.02	/
	1 st migration 2 nd migration 3 rd migration Limit	Specific migration of Bisphenol A(BPA)/ (mg/kg) 3% Acetic acid,70°C,2h 1st migration N.D. 2nd migration N.D. 3rd migration N.D. Limit 0.05

	Test Result		
Test point	Specific migration of Bisphenol A(BPA)/ (mg/kg)	Conclusion	
	3% Acetic acid,70°C,2h		
1-2	N.D.	Conformity	
Limit (Client's Requirement)	0.05	/	
MDL	0.02	/	






-Specific migration of Primary aromatic amines

Test Item(s)	MDL (mg/kg)	Limit (mg/kg)
4-Aminobiphenyl	0.002	N.D.
Benzidine	0.002	N.D.
4-Chloro-o-Toluidine	0.002	N.D.
2-Naphthylamine	0.002	N.D.
4-amino-2',3-dimethylazobenzene	0.002	N.D.
5-Nitro-o-toluidine	0.002	N.D.
4-Chloroaniline	0.002	N.D.
4-Methoxy-m-phenylenediamine	0.002	N.D.
4,4'-Diaminodiphenylmethane	0.002	N.D.
3,3'-Dichlorobenzidine	0.002	N.D.
3,3'-Dimethoxybenzidine	0.002	N.D.
3,3'-Dimethybenzidine	0.002	N.D.
4,4'-Methylenedi-o-toluidine	0.002	N.D.
6-methoxy-m-toluidine	0.002	N.D.
4,4'-methylenebis[2-chloroaniline]	0.002	N.D.
4,4'-Oxydianiline	0.002	N.D.
4,4'-Thiodianiline	0.002	N.D.
2-Aminotoluene	0.002	N.D.
4-methyl-m-phenylenediamine	0.002	N.D.
2,4,5-Trimethylaniline	0.002	N.D.
2-Methoxyaniline	0.002	N.D.
4-Aminoazobenzene	0.002	N.D.
1,3 phenylenediamine	0.002	N.D.
Total of other primary aromatic amines	0.01	0.01



	Test Result (mg/kg)		
Test Item(s)	1-1		
	3% Acetic acid 70°C, 2h		
4-Aminobiphenyl	N.D.		
Benzidine	N.D.		
4-Chloro-o-Toluidine	N.D.		
2-Naphthylamine	N.D.		
4-amino-2',3-dimethylazobenzene	N.D.		
5-Nitro-o-toluidine	N.D.		
4-Chloroaniline	N.D.		
4-Methoxy-m-phenylenediamine	N.D.		
4,4'-Diaminodiphenylmethane	N.D.		
3,3'-Dichlorobenzidine	N.D.		
3,3'-Dimethoxybenzidine	N.D.		
3,3'-Dimethybenzidine	N.D.		
4,4'-Methylenedi-o-toluidine	N.D.		
6-methoxy-m-toluidine	N.D.		
4,4'-methylenebis[2-chloroaniline]	N.D.		
4,4'-Oxydianiline	N.D.		
4,4'-Thiodianiline	N.D.		
2-Aminotoluene	N.D.		
4-methyl-m-phenylenediamine	N.D.		
2,4,5-Trimethylaniline	N.D.		
2-Methoxyaniline	N.D.		
4-Aminoazobenzene	N.D.		
1,3 phenylenediamine	N.D.		
Total of other primary aromatic amines	N.D.		
Conclusion	Conformity		





-Specific migration of Heavy metals

Test Item(s)	T4 1242 1		Test Result(s) (mg/kg) 1-1			Limit (mg/kg)
	Test condition/ Equipment	MDL (mg/kg)				
	Equipment	(mg/ng)	1 st migration	2 nd migration	3 rd migration	(g/.kg)
Barium (Ba)		0.1	N.D.	N.D.	N.D.	1
Cobalt (Co)		0.01	N.D.	N.D.	N.D.	0.05
Copper (Cu)		0.25	N.D.	N.D.	N.D.	5
Iron (Fe)		0.25	N.D.	N.D.	N.D.	48
Lithium (Li)		0.1	N.D.	N.D.	N.D.	0.6
Manganese (Mn)		0.1	N.D.	N.D.	N.D.	0.6
Zinc (Zn)		0.25	N.D.	N.D.	N.D.	5
Aluminum (Al)		0.1	N.D.	N.D.	N.D.	1
Europium (Eu)		0.01	N.D.	N.D.	N.D.	/
Gadolinium (Gd)		0.01	N.D.	N.D.	N.D.	/
Lanthanum (La)		0.01	N.D.	N.D.	N.D.	/
Terbium (Tb)		0.01	N.D.	N.D.	N.D.	/
Sum(Eu+Gd+La+Tb)	3% Acetic acid/	/	N.D.	N.D.	N.D.	0.05
Antimony (Sb)	70°C, 2h/ ICP-OES/ IC	0.01	N.D.	N.D.	N.D.	0.04
Arsenic (As)		0.01	N.D.	N.D.	N.D.	N.D.
Cadmium (Cd)		0.002	N.D.	N.D.	N.D.	N.D.
Chromium (Cr)		0.01	N.D.	N.D.	N.D.	N.D.
Lead (Pb)		0.01	N.D.	N.D.	N.D.	N.D.
Mercury (Hg)		0.01	N.D.	N.D.	N.D.	N.D.
Nickel (Ni)		0.01	N.D.	N.D.	N.D.	0.02
Conclusion		/		Conformity		/
Ammonium (NH ₄ ⁺)		0.10	N.D.	N.D.	N.D.	/
Calcium (Ca)		0.01	0.020	N.D.	0.254	/
Magnesium (Mg)		0.01	N.D.	N.D.	0.034	/
Potassium (K)		0.01	N.D.	N.D.	0.034	/
Sodium (Na)		0.01	N.D.	N.D.	0.065	/



Unit: %

Test item(s)	Test Condition	MDL	Result(s) 1-2	Limit
Volatile Organic Matter	200°C, 4h	0.1	0.12	0.5
Conclusion	200 C, 4n	/	Conformity	/


- Peroxide value

Unit: %

Test Item N	MDL	Result(s)	Limit
	WIDL	1-2	Limit
Peroxide value	0.2	N.D.	Absent
Conclusion	/	Conformity	/


- Specific Migration of Organotin (measured as Tin)

Test point	Test Result	Conclusion
	Specific Migration of Organotin (measured as Tin)/ (mg/kg)	
	3% Acetic acid, 70°C,2h	
1-2	N.D.	Conformity
Limit	0.1	/
MDL	0.01	/







Test Flow Chart of Heavy Metal Content




Test Flow Chart of Phthalates









Test Flow Chart of Polycyclic-aromatic Hydrocarbons (PAHs)









Test Flow Chart of Pentachlorophenol (PCP)







Test Flow Chart of Formaldehyde Release





Conditions of Issuance of Test Reports

- 1. All samples and goods are accepted by the Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd. (the "Company") solely for testing and reporting in accordance with the following terms and conditions. The company provides its services on the basis that such terms and conditions constitute express agreement between the company and any person, firm or company requesting its services (the "Clients").
- 2. Any report issued by Company as a result of this application for testing services (the "Report") shall be issued in confidence to the Clients and the Report will be strictly treated as such by the Company. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of the Company. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Company to its customer, supplier or other persons directly concerned. The Company will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the Report, unless required by the relevant governmental authorities, laws or court orders.
- 3. The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.
- 4. In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate.
- 5. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.
- 6. The Company will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations. 7. Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.
- 8. The Company is not responsible for recalling the electronic version of the original report when any revision is made to them. The Client assumes the responsibility to providing the revised version to any interested party who uses them.
- 9. Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.

*** End of Report ***